

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1-3. (Canceled)

4. (Currently amended) A fiber reinforced plastic comprising:

a thermoset shape memory polymer composition as a matrix resin comprising a liquid isocyanate which is bifunctional or trifunctional or a mixture of bifunctional and trifunctional isocyanates, and a polyol having an average molecular weight of from 100 to 250, ~~550~~, with a molar ratio in terms of functional groups of isocyanate : polyol = 0.9 to 1.1 : 1.0, wherein a cured product of the thermoset shape memory polymer composition has a glass transition point (T_g) of 40 70 to 150°C; and

a fibrous material.

5. (Currently amended) A fiber reinforced plastic according to claim 4, which contains 25 to 95 vol. % of the thermoset shape memory polymer composition and 5 to 75 vol. % of the fibrous material.

6. (Currently amended) A production process of a fiber reinforced plastic, which comprises:

preparing a thermoset shape memory polymer composition having a liquid bifunctional isocyanate and/or a liquid trifunctional isocyanate and a polyol having an average molecular weight of from 100 to 250, ~~550~~, with a molar ratio in terms of functional groups of isocyanate : polyol = 0.9 to 1.1 : 1.0, wherein a cured product of the thermoset shape memory polymer composition has a glass transition point (T_g) of 40 70 to 150°C;

impregnating a fibrous material with a matrix resin of the composition; and then

curing the impregnated fibrous material.

7. (Original) A production process of a fiber reinforced plastic according to claim 6, wherein the polyol contains at least 50 wt.% of polypropylene glycol.

8. (Original) A production process of a fiber reinforced plastic according to claim 7, wherein the polyol is bifunctional.

9. (Original) A production process of a fiber reinforced plastic according to any one of claims 6 to 8, wherein at least two layers of the impregnated fibrous material were stacked one after another, caused to stick closely each other, pressurized and cured as a laminate having a multilayer structure.

10. (Previously presented) A fiber reinforced plastic according to claim 4, wherein the polyol contains at least 50 wt.% of polypropylene glycol.

11. (Previously presented) A fiber reinforced plastic according to claim 4, wherein the polyol is bifunctional.

12. (Currently amended) A production process of a fiber reinforced plastic according to claim 6, which contains 25 to 95 vol. % of the thermoset shape memory polymer composition and 5 to 75 vol. % of the fibrous material.

13. (Canceled)

14. (Previously presented) A fiber reinforced plastic according to claim 4, wherein the average molecular weight is from 100 to 250 and the T_g is from 70 to 150°C.

15. (Previously presented) A production process according to claim 6, wherein the average molecular weight is from 100 to 250 and the T_g is from 70 to 150°C.

16. (Previously presented) A production process according to claim 6, wherein the fibrous material with a matrix resin of the composition is molded by a resin transfer molding.

17. (New) A fiber reinforced plastic according to claim 4, wherein the average molecular weight is from 150 to 250 and the T_g is from 70 to 120°C.

18. (New) A production process according to claim 6, wherein the average molecular weight is from 150 to 250 and the Tg is from 70 to 120°C.

19. (New) A fiber reinforced plastic comprising:

a thermoset shape memory polymer composition as a matrix resin comprising a liquid isocyanate which is bifunctional or trifunctional or a mixture of bifunctional and trifunctional isocyanates, and a polyol having an average molecular weight of from 100 to 550, with a molar ratio in terms of functional groups of isocyanate : polyol = 0.9 to 1.1 : 1.0, wherein the polyol contains at least 50 wt.% of polypropylene glycol, and wherein a cured product of the thermoset shape memory polymer composition has a glass transition point (Tg) of 70 to 150°C; and

a fibrous material.

20. (New) A production process of a fiber reinforced plastic comprising:

preparing a thermoset shape memory polymer composition having a liquid bifunctional isocyanate and/or a liquid trifunctional isocyanate and a polyol having an average molecular weight of from 100 to 550, with a molar ratio in terms of functional groups of isocyanate : polyol = 0.9 to 1.1 : 1.0, wherein the polyol contains at least 50 wt.% of polypropylene glycol, and wherein a cured product of thermoset shape memory polymer composition has a glass transition point (Tg) of 70 to 150°C;

impregnating a fibrous material with a matrix resin of the composition; and then

curing the impregnated fibrous material.